







# Technical data sheet

## **PROTECT 310**





### Acrylic filler

PROPERTIES		
PROTECT 310 acrylic filler – a highly filling primer based on acrylic resins. Thanks to a high spray viscosity, the product can be applied in very thick layers that perfectly repair even relatively large scratches and irregularities of substrate. The product has a very good adhesion to various substrates; thanks to high quality resins and special additives, it provides good anti-corrosion protection and insulation of polyester materials (putties) from topcoats. Available in three colours: white, grey and black; mixing white and black allows producing any shade of grey.		
RELATED PRODUCTS		
H 5520	Hardener	
THIN 850	Acrylic thinner Standard, Fast and Slow	
PLUS 770	Elasticity increasing agent	LT-04-01
PLUS 750	Acrylic accelerating agent	LT-04-02
PLUS 760	Antisilicone additive	LT-04-04
SUBSTRATES		
Old paint coatings, including thermoplastic paints	Degrease, dry sand with P220 – P280, blow off, degrease again.	
Polyester putties	Dry sand, use P240 - P320 for final sanding, blow off, degrease.	
Epoxy primers	Up to 12 hours without sanding, after 12 hours sand dry with P320, blow off, degrease.	
Steel	Degrease and dry sand with P120.	
Stainless steel	Degrease.	
Wash primers	Apply after drying.	
Plastics	Degrease with the PLUS 780 degreaser, mat with a needled cloth, degrease again. Use the PLUS 700 adhesion increasing agent. Use the PLUS 770 elasticity increasing agent if necessary.	
Polyester laminates	Degrease, dry sand with P280, blow off, degrease again.	

04/02/2010

MIXING RATIO					
	PROTECT 310 H 5520 THIN 850	Filling version		Priming version	
		Volume ratio	Weight ratio	Volume ratio	Weight ratio
		4	100	4	100
		1	15	1	15
		10	5	20	11
Apply the thinner in the amount calculated for the primer.					
VISCOSITY					
	DIN 4/20°C	Filling version		Priming version	
		approx. 60 s		approx. 40 s	
CONTENT OF VOLATILE ORGANIC COMPOUNDS					
VOC II/B/c limit*		540 g/l			
Actual VOC content		500 g/l			
* For ready to use mixture acc. to EU Directive 2004/42/CE					
APPLICATION CONDITIONS					
It is recommended to apply the primer should at a temperature above 15°C and a humidity of no more than 80 %.					
APPLICATION					
	Conventional gravity fed spray gun	Nozzle	Pressure	Distance	
		1.6 – 1.8mm	3 – 4 bar	15 – 20 cm	
CAUTION: Instructions of the equipment manufacturer must be followed.	Low-pressure spray gun, HVLP, gravity-fed	1.6 – 1.7 mm	2 bar	10 – 15 cm	
	Number of layers	2–3			
	Single dry layer thickness	50 – 60 µm			
	The yield of the ready to use mixture for the given range of dry layer thickness	4.5 m²/l at 100 µm			
	Mixture life at 20°C	1 h			
	Flash off time between layers at 20°C	5 –10 min			

0-9/02/2010

CURING TIMES			
	20°C	60°C	
	3 h	30 min	
CAUTION: The curing times apply to the temperatures of the individual elements.			
IR DRYING			
	Distance	Follow the recommendations of the equipment manufacturer	
	Time depending on the type and power of the lamp	10 — 20 min	
CAUTION: Start IR heating no sooner than 10 mins after applying the last layer.			
SANDING			
	Dry sanding	P360 — P500	
	Wet sanding	P600 — P1000	
THIN 850 ACRYLIC THINNER			
Surface	15 — 20°C	20 — 25°C	25 — 35°C
Small 1-2 elements spot repair	THIN 850 Fast	THIN 850 Fast	THIN 850 Standard
Medium 3-5 elements	THIN 850 Fast / Standard	THIN 850 Standard	THIN 850 Slow
Large more than 5 elements	THIN 850 Standard / Slow	THIN 850 Slow	THIN 850 Slow
COLOUR			
White, grey, black.			
EQUIPMENT CLEANING			
THIN 850 acrylic thinner or NC solvent.			
STORAGE CONDITIONS			
Store in a cool dry room, away from sources of fire and heat. Avoid direct exposure to sunlight.			
SHELF LIFE			
PROTECT 310	24 months/20°C		
H 5520	12 months/20°C		
THIN 850	24 months/20°C		

**SAFETY**

See Safety Data Sheet.

**NOTES**

Use PROTECT 310 with NOVOL H 5520 hardener only.

Use of other hardeners may reduce the anti-corrosion properties and the chemical and mechanical resistance of the filler.

**OTHER INFORMATION**

The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.

ADDITIONAL INFORMATION			
<b>WEIGHT QUANTITY OF COMPONENTS:</b> <b>Filling version 4+1+10%</b> <b>CAUTION!</b> In order to obtain a primer with appropriate parameters it is very important to exactly dose the individual components.			
Mixture quantity	PROTECT 310	H 5520	THIN 850
0.10 l	125 g	18.4 g	6.6 g
0.15 l	187 g	28 g	10 g
0.20 l	249 g	37 g	13 g
0.25 l	312 g	46 g	17 g
0.30 l	374 g	55 g	20 g
0.40 l	499 g	74 g	26 g
0.50 l	623 g	92 g	33 g
0.75 l	935 g	138 g	49 g
1.00 l	1247 g	184 g	66 g

<b>WEIGHT QUANTITY OF COMPONENTS:</b> <b>Priming version 4+1+20%</b> <b>CAUTION!</b> In order to obtain a primer with appropriate parameters it is very important to exactly dose the individual components.			
Mixture quantity	PROTECT 310	H 5520	THIN 850
0.10 l	116 g	17 g	12 g
0.15 l	174 g	26 g	18 g
0.20 l	232 g	34 g	25 g
0.25 l	290 g	43 g	31 g
0.30 l	348 g	52 g	37 g
0.40 l	464 g	69 g	49 g
0.50 l	580 g	86 g	61 g
0.75 l	871 g	129 g	92 g
1.00 l	1161 g	172 g	123 g